



CERTIFICATE OF TESTING

For the Account Of: Creation Baumann
979 Third Avenue
Suite 1522
New York, NY 10022
Contact: Ellen Shultz

Client's Identification: Cavallo Piu

TEST PERFORMED Breaking Strength and Elongation of Textile Fabrics (Grab Test) ASTM D5034-09(2013)(G-E)

TEST RESULTS

| Specimen | Breaking Force (lbf) | |
|----------|-------------------------|-----------------|
| 1 | 84 | |
| 2 | 77 | |
| 3 | 82 | |
| 4 | 85 | |
| 5 | 74 | |
| | | Avg of Warp: 80 |
| 6 | 62 | |
| 7 | 52 | |
| 8 | 63 | |
| 9 | 63 | |
| 10 | 62 | |
| 11 | 62 | |
| 12 | 65 | |
| 13 | 63 | |
| | | Avg of Fill: 61 |

NOTES

Equipment Used: Tinius Olson H5KT Universal Testing Machine
Load Cell Maximum: 1000 pounds
Jaw Size: 1 inch x 1 inch (face and back), rubber coated
Test Conditions: 70 ±2°F, 65 ±2% Relative Humidity
Sampling Method: As Received

ACCEPTANCE CRITERIA

| A.C.T. Standard | Acceptance Criteria |
|------------------------------|---------------------|
| Upholstery | 50 pounds minimum |
| Panels and Upholstered Walls | 35 pounds minimum |

CERTIFICATION I certify that the above results were obtained after testing specimen in accordance with the procedures and equipment specified by the standard stated above.

Berta Stiver

Authorized Signature-MB



TEXTILE TESTING
CERTIFIED BEAUTY



TESTING CERT. #3193.01

Report Number: 68417
Date: 10-22-2014

CERTIFICATE OF TESTING

For the Account Of: Creation Baumann
979 Third Avenue
Suite 1522
New York, NY 10022
Contact: Ellen Shultz

Client's Identification: Cavallo Piu

TEST PERFORMED Pilling Resistance and Other Related Surface Changes of Textile Fabrics: Brush Pilling Tester
ASTM D3511/D3511M-13

TEST RESULTS

| | Rating |
|---------|--------|
| Left | 4.0 |
| Center | 4.0 |
| Right | 4.0 |
| Average | 4.0 |

*NOTE: Extremely severe fuzzing

RATING SYSTEM

- Class 5.0 No Pilling
- Class 4.0 Slight Pilling
- Class 3.0 Moderate Pilling
- Class 2.0 Severe Pilling
- Class 1.0 Very Severe Pilling

NOTES

Test Conditions: 70 ±2°F, 65 ±2% Relative Humidity
Sampling Method: As Received
Viewing Apparatus: Macbeth Lightbooth
Viewing Option: 45 degree
Rating Standard: ADJD3512 Photographic Standards
Running Times: 4 minutes brushing / 2 minutes pilling

ACCEPTANCE CRITERIA

A.C.T. Standard: Acceptance Criteria
Upholstery Class 3 minimum

CERTIFICATION I certify that the above results were obtained after testing specimen in accordance with the procedures and equipment specified by the standard stated above.

Berta Stiver

Authorized Signature-MB



CERTIFICATE OF TESTING

For the Account Of: Creation Baumann
979 Third Avenue
Suite 1522
New York, NY 10022
Contact: Ellen Shultz

Client's Identification: Cavallo Piu

TEST PERFORMED California Technical Bulletin 117: June 2013 – Requirements, Test Procedure and Apparatus for Testing the Smolder Resistance of Materials Used in Upholstered Furniture – Cover Fabric Test

TEST RESULTS

| Specimen | Char Length (in) | Extinguished in 45 minutes? (Y/N) |
|----------|------------------|-----------------------------------|
| 1 | 0.5 | Y |
| 2 | 0.6 | Y |
| 3 | 0.5 | Y |

NOTES

Test Conditions: 70 ±5°F, 50 ±5% Relative Humidity

ACCEPTANCE CRITERIA

A material is considered to pass or fail based on the following criteria:

1. A single mock-up test specimen fails to meet the requirements of this test procedure if any of the following criteria occurs:
 - a. The mock-up test specimen continues to smolder after the 45 minute test duration
 - b. A vertical char length of more than 1.8 inches (45mm) develops on the cover fabric
 - c. The mock-up test specimen transitions to open flaming
2. The cover fabric passes the test if three initial mock-up specimens pass the test, i.e. the cigarettes burn their full length and are no longer smoldering
3. If more than one initial specimen fails, the cover fabric fails the test
4. If any one of the three initial specimens fails, repeat the test on additional three specimens
5. If all three additional specimens pass the test, the cover fabric passes the test. If any one of the additional three specimens fails, the cover fabric fails the test

CONCLUSION

Based on the above Results and Acceptance Criteria, the item tested is:

- Pass
 Fail

CERTIFICATION I certify that the above results were obtained after testing specimen in accordance with the procedures and equipment specified by the standard stated above.

Berta Stiver

Authorized Signature-MB



TEXTILE TESTING
CERTIFIED BEAUTY



TESTING CERT. #3193.01

Report Number: 68417
Date: 10-22-2014

CERTIFICATE OF TESTING

For the Account Of: Creation Baumann
979 Third Avenue
Suite 1522
New York, NY 10022
Contact: Ellen Shultz

Client's Identification: Cavallo Piu

TEST PERFORMED Colorfastness to Light AATCC Test Method 16.3-2012, Option 3

TEST RESULTS

| | |
|-----------|-----------------|
| Rating | Number Of Hours |
| Class 4.0 | 40 |

RATING SYSTEM

- Class 5 No fading or color change
- Class 4 Slight fading or color change
- Class 3 Noticeable fading or color change
- Class 2 Considerable fading or color change
- Class 1 Much fading or color change

NOTES

Light Source: Xenon –Arc, Water Cooled, Continuous Light
Scale Used for Evaluation: AATCC Gray Scale for Color Change

ACCEPTANCE CRITERIA

| | |
|------------------------------|----------------------------|
| A.C.T. Standard | Acceptance Criteria |
| Upholstery | Class 4 minimum – 40 hours |
| Direct Glue Wallcoverings | Class 4 minimum – 40 hours |
| Panels and Upholstered Walls | Class 4 minimum – 40 hours |
| Drapery | Class 4 minimum – 60 hours |

CERTIFICATION I certify that the above results were obtained after testing specimen in accordance with the procedures and equipment specified by the standard stated above.

Berta Stiver

Authorized Signature-MB



TEXTILE TESTING
CERTIFIED BEAUTY



TESTING CERT. #3193.01

Report Number: 68417
Date: 10-22-2014

CERTIFICATE OF TESTING

For the Account Of: Creation Baumann
979 Third Avenue
Suite 1522
New York, NY 10022
Contact: Ellen Shultz

Client's Identification: Cavallo Piu

TEST PERFORMED Colorfastness to Wet & Dry Crocking AATCC 8-2013

TEST RESULTS

| | |
|--------------|-----------|
| Dry Crocking | Class 5.0 |
| Wet Crocking | Class 4.5 |

RATING SYSTEM

- Class 5 No color transfer
- Class 4 Slight color transfer
- Class 3 Moderate color transfer
- Class 2 Considerable color transfer
- Class 1 Much Color transfer


NOTES

Scale Used for Evaluating: AATCC Chromatic Transference Scale

ACCEPTANCE CRITERIA

| A.C.T. Standard | Acceptance Criteria (Dry) | Acceptance Criteria (Wet) |
|------------------------------|---------------------------|---------------------------|
| Upholstery | Class 4 minimum | Class 3 minimum |
| Direct Glue Wallcoverings | Class 3 minimum | Class 3 minimum |
| Panels and Upholstered Walls | Class 3 minimum | Class 3 minimum |
| Drapery (Solid) | Class 4 minimum | Class 3 minimum |
| Drapery (Print) | Class 4 minimum | Class 3 minimum |

CERTIFICATION I certify that the above results were obtained after testing specimen in accordance with the procedures and equipment specified by the standard stated above.


Authorized Signature-MB



CERTIFICATE OF TESTING

For the Account Of: Creation Baumann
979 Third Avenue
Suite 1522
New York, NY 10022
Contact: Ellen Shultz

Client's Identification: Cavallo Piu

TEST PERFORMED Resistance to Slippage of Yarns in Woven Fabrics Using a Standard Seam ASTM D4034-92

TEST RESULTS

| Specimen | Warp Yarn Slippage (lbf) | | Fill Yarn Slippage (lbf) | |
|----------|--------------------------|----|--------------------------|----|
| 1 | 92.1 | SB | 71.0 | SB |
| 2 | 95.8 | SB | 70.4 | SB |
| 3 | 90.1 | SB | 67.0 | SB |
| 4 | 88.5 | SB | 62.6 | SB |
| 5 | 95.1 | SB | 68.0 | SB |
| Average | 92.3 | | 67.8 | |

ABBREVIATIONS USED

- SB Seam broke before 1/4" slippage - Results should reflect this
- SS 1/4" slippage occurred - Note: Actual slippage of yarns is visible
- FB Fabric broke before 1/4" slippage - Note: Actual breakage is visible

NOTES

Equipment Used: Tinius Olson H5KT Universal Testing Machine
Seam Description: Per ASTM D4034-92
Seam Type: Standard Lockstitch
Stitches per Inch: 7 ± 0.5 stitches per inch
Needle Used: Size 22 NM: 140, 135x17 ball point needle
Thread: Nymo EX Bonded Nylon thread; 5x is used for the bobbin and 8x is used for the needle

ACCEPTANCE CRITERIA

A.C.T. Standard Upholstery: Acceptance Criteria 25 lbs. Minimum

CERTIFICATION I certify that the above results were obtained after testing specimen in accordance with the procedures and equipment specified by the standard stated above.

Berta Stiver

Authorized Signature-MB



CERTIFICATE OF TESTING

For the Account Of: Creation Baumann
979 Third Avenue
Suite 1522
New York, NY 10022
Contact: Ellen Shultz

Client's Identification: Cavallo Piu

TEST PERFORMED Abrasion Resistance of Textile Fabrics (Oscillatory Cylinder Method) ASTM D4157-13

TEST RESULTS

| | | |
|---------------------------------|---|--|
| Number of Double Rubs 50,000 | Warp (Length) Specimens Moderate Wear* | Fill (Width) Specimens Moderate Wear* |
|---------------------------------|---|--|

*NOTE: Extremely severe pilling

INTERPRETATION USED

- Option 1 The end point is reached on a woven fabric when two or more yarns have broken or on a knitted fabric, when a hole appears.
- Option 2 The end point is reached when there is a change in shade or appearance that is sufficient to cause a customer to complain.

NOTES

Abradant Used: ACT Standard #10 Cotton Duck Wire Screen
 Samples Backed with Masking Tape: Yes No
 Tension: 4 pounds
 Compression: 3 pounds

ACCEPTANCE CRITERIA


| | |
|-----------------------------|--|
| A.C.T. Standard | Acceptance Criteria |
| General Contract Upholstery | No appreciable breakage or wear after 15,000 double rubs |
| Heavy Duty Upholstery | No appreciable breakage or wear after 30,000 double rubs |

CONCLUSION

Based on the above Results and the A.C.T. Standard, the item tested:

- Unrated
- General Contract Upholstery
- Heavy Duty Upholstery

CERTIFICATION I certify that the above results were obtained after testing specimen in accordance with the procedures and equipment specified by the standard stated above.


Authorized Signature-MB