

Airflow resistance on the base* of DIN EN 29053 (ISO 9053)

Measurement of specific airflow resistance R_s

A 03 E

Measuring sample:

Name: GORDON 33

Description: acoustic fabric

Manufacturer: création baumann Weberei und Färberei AG
CH-4901 Langenthal

Client of measurement: manufacturer



Measuring conditions:

Standard: DIN EN 29053: Materials for acoustical applications; Determination of airflow resistance (ISO 9053)

Method: direct-airflow method, measurement at 10 different airflow velocities and extrapolation to an airflow velocity of 0,5 mm/s

Specimen holder: round, Diameter 112,8 mm

Temperature: 23 °C

Relative humidity: 40 %

Measurement date: 2010-03-01

Specimen:

Number of specimen: 1 of 2

Diameter: 112,8 mm

Effective cross section: 100,00 cm²


Thickness: -

Measurement setup: specimen (ca. 240 mm x 200 mm) fit in specimen holder

* required number of specimens according to ISO 9053: 3 x 3 = 9

Measurement result:

	u	Δp	R_s
Measuring values	149,9	191,4	1276,7
	135,7	173,8	1280,9
	121,4	155,1	1277,4
	107,2	136,4	1273,0
	92,9	118,1	1270,5
	78,5	98,8	1259,1
	64,3	80,1	1245,7
	50,1	61,4	1226,0
	35,7	43,1	1207,1
	Extrapolation	0,5	



Airflow velocity u in mm/s
 Pressure difference over specimen Δp in Pa
 Specific airflow resistance R_s in Pa·s/m

Measuring result: Specific airflow resistance R_s = 1201,3 Pa·s/m

Gesellschaft für Akustikforschung Dresden mbH
 Blumenstraße 80
 01307 Dresden
 Phone: +49 (0)351 811309-40, Fax: -50

Report-No.: 100050053501-A03E
 Editor: C. Schulze, V. Bormann
 Date: 2010-03-05