

Measuring sample:

Name: **SCHERZO III**
Description: acoustic fabric
Manufacturer: création baumann Weberei und Färberei AG, CH-4901 Langenthal
Client of measurement: manufacturer

Measuring conditions:

Standard: DIN EN 29053: Materials for acoustical applications; Determination of airflow resistance (ISO 9053)
Method: direct-airflow method, measurement at 5 different airflow velocities and extrapolation to an airflow velocity of 0,5 mm/s
Specimen holder: round, 112,8 mm diameter
Temperature: 22 °C
Relative humidity: 56 %
Measurement date: 2006-03-31

Specimen:

Total number: 1
Shape: specimen (ca. 200 mm x 180 mm) fit in specimen holder
Effective cross section: 100 cm²

Single Results:

Specimen	Nr. 1		
	u	Δp	R_s
Measuring values	37,6	0,193	5,1
	30,6	0,146	4,8
	23,9	0,105	4,4
	17,5	0,0791	4,5
	11,1	0,0498	4,5
Extrapolation	0,5		4,1

(Airflow velocity u in mm/s, pressure difference Δp over specimen in Pa, specific airflow resistance R_s in Pa s/m)

Measuring result:

Specific airflow resistance $R_s = 4,1$ Pa s/m
--