

Our Ref: SW/PN/BR

03 February 2015

**Report 249136**

**Page 1 of 2**

Creation Baumann  
Unit 302 Business Design Centre  
52 Upper Street  
London  
N1 0QH

Contact: Anna Ascjak

---

DATE RECEIVED	:	27 JANUARY 2015
QUALITY/REFERENCE	:	SECRET
REPUTED FIBRE CONTENT	:	100% POLYESTER FR
FABRIC DESCRIPTION	:	WOVEN
COLOUR/DESIGN	:	GREY
ORDER NUMBER	:	L0851145
PERFORMANCE STANDARD	:	GENERAL

---

REQUEST: BS 5867 - 2:2008 Fabrics for curtains, drapes and window blinds – Part 2:  
Flammability requirements - Specification


---

COMMENT: The sample submitted complies with the flammability requirements of BS5867-  
2:2008 for Type B performance.

---



**S. WISEMAN**  
**LABORATORY MANAGER**



**P. NEESAM**  
**HEAD OF FLAMMABILITY**

*This report shall not be reproduced except in full without written approval of HSTTS. In all circumstances results of tests are implied as referring only to the sample supplied and should not be construed or interpreted on any other basis. The comments given in the report are for guidance only and are not a part of the results, Opinions and interpretations expressed herein are outside the scope of UKAS accreditation*



Our Ref: SW/PN/BR

03 February 2015

**Report 249136**

**Page 2 of 2**

**FIRE TESTS ACCORDING TO BS 5867 - 2:2008**

**Fabrics for curtains, drapes and window blinds – Part 2: Flammability requirements - Specification**

**Procedure**

Specimens of Fabric, Ref: Secret were subjected to the test method as described in BS EN ISO 15025:2002, procedure “A” Surface ignition. The samples were tested in the ‘as received’ state only, after being conditioned for 24 hours in an atmosphere having a temperature of  $20 \pm 2^{\circ}\text{C}$  and a relative humidity of  $65 \pm 5\%$ .

Pre-treatment: None

Type B performance requirements

No part of any hole nor any part of the lowest boundary of any flame shall reach the top edge or either vertical edge of the sample. If any part of any hole or any part of the lowest boundary of any flame, reaches the top edge or either vertical edge, or if there is any separation of any flaming debris droplets in the testing of one specimen, a further six specimens shall be tested. If all six new specimens comply with the above requirements, the fabric shall be deemed to conform to the requirements for type “B” of the above standard.

**Results**

The following test results relate only to the ignitability of the combination of materials under the particular conditions of test; they are not intended as a means of assessing the full potential fire hazard of the materials in use.

They also only relate to the materials tested. They do not guarantee to represent the performance of production materials.

Original condition	Warp/Length			Weft/Width		
	1 ↑	2 ↓	3 ↑	1 →	2 ←	3 →
Flames reached edge?	No	No	No	No	No	No
Hole reached edge?	No	No	No	No	No	No
Flaming debris?	No	No	No	No	No	No
Duration of afterflame, s	0.0	0.0	0.0	0.0	0.0	0.0
Duration of afterglow, s	0.0	0.0	0.0	0.0	0.0	0.0

**Comments**

The sample submitted complies with the flammability requirements for Type B performance.