

**LICHTECHTHEIT TEST
LIGHTFASTNESS TEST**

Artikel/Article:	ULTRA V
Artikel-Nr./Article No.:	2060

Col.-Nr. Col.-No.	Note/Result ¹ nach 100 Stunden after 100 hours	Note/Result ¹ nach 200 Stunden after 200 hours
102		6-7
105		6-7
112		7
113		7
115		5-6
116		4
122		6
123		6
124		6
225		7
229		7
236		6
300		7
306		6
308		6-7
313		6
324		7
336		5
337		5
401		6
402		7
403		5-6
404		5
405		6
406		6
408		6
410		5-6

Col.-Nr. Col.-No.	Note/Result ¹ nach 100 Stunden after 100 hours	Note/Result ¹ nach 200 Stunden after 200 hours
413		7
414		7
415		7
416		7
417		6
418		7
419		7
423		6
432		6
436		6
437		6
439		7
440		7
441		7
443		6
444		5-6
445		5-6
446		6
447		6
448		7
450		7
501		7
502		5-6
503		5
504		5-6
505		5
506		5

¹ Lichtechtheit nach Xenon-Test ISO 105-B02 / Light fastness after Xenon-Test ISO 105-B02

**LICHTECHTHEIT TEST
LIGHTFASTNESS TEST**

Col.-Nr. Col.-No.	Note/Result ¹ nach 100 Stunden after 100 hours	Note/Result ¹ nach 200 Stunden after 200 hours
507		5-6
508		7
509		5-6
510		5
511		4-5
512		5
513		5
515		4-5
516		5-6
517		4
518		6-7
519		7

Col.-Nr. Col.-No.	Note/Result ¹ nach 100 Stunden after 100 hours	Note/Result ¹ nach 200 Stunden after 200 hours
520		7
521		5
522		7
523		7
525		5
526		4
527		6
528		7
529		7
530		7
531		7