

**LICHTECHTHEIT TEST  
LIGHTFASTNESS TEST**

Artikel/Article:	UNISONO IV
Artikel-Nr./Article No.:	4000/4001

Col.-Nr. Col.-No.	Note/Result <sup>1</sup> nach 100 Stunden after 100 hours	Note/Result <sup>1</sup> nach 200 Stunden after 200 hours
10		6
11		6
13		6
44		6
48		6
64		6
83		6
86		6
87		6
88		6
90		6
92		6
93		6
94		6
96		6
97		6
100		6
210		7
224		7
233		7
234		7
302		4-5
303		6
304		6
305		6
307		5-6
310		5

Col.-Nr. Col.-No.	Note/Result <sup>1</sup> nach 100 Stunden after 100 hours	Note/Result <sup>1</sup> nach 200 Stunden after 200 hours
312		6
314		6-7
315		6
318		5
319		6-7
324		6
325		6-7
343		6-7
350		6-7
351		6-7
401		5-6
402		5-6
403		5-6
404		5-6
405		5-6
406		5-6
407		5-6
408		5-6
409		5-6
410		5-6
411		5-6
412		5-6
413		5-6
414		5-6
415		5-6
416		4-5
417		4-5

<sup>1</sup> Lichtechtheit nach Xenon-Test ISO 105-B02 / Light fastness after Xenon-Test ISO 105-B02

**LICHTECHTHEIT TEST  
LIGHTFASTNESS TEST**

Col.-Nr. Col.-No.	Note/Result <sup>1</sup> nach 100 Stunden after 100 hours	Note/Result <sup>1</sup> nach 200 Stunden after 200 hours
418		5-6
419		4-5
420		5-6
421		5-6
422		5-6
423		5-6
424		5-6
425		5-6
426		5-6
427		5-6

Col.-Nr. Col.-No.	Note/Result <sup>1</sup> nach 100 Stunden after 100 hours	Note/Result <sup>1</sup> nach 200 Stunden after 200 hours
428		5-6
430		5-6
431		5-6
432		5-6
433		5-6
434		5-6
435		5-6