

**LICHTECHTHEIT TEST
LIGHTFASTNESS TEST**

Artikel/Article:	VELLING III
Artikel-Nr./Article No.:	35300

Col.-Nr. Col.-No.	Note/Result¹ nach 100 Stunden after 100 hours	Note/Result¹ nach 200 Stunden after 200 hours
364		6-7
366		5
370		6
376		6-7
377		6-7
379		6-7
393		5
394		5
397		6-7
401		6
451		4-5
452		4-5
453		4-5
454		4-5
455		4-5
456		4-5
457		4-5
458		4-5

Col.-Nr. Col.-No.	Note/Result¹ nach 100 Stunden after 100 hours	Note/Result¹ nach 200 Stunden after 200 hours
459		4-5
460		4-5
461		4-5
462		4-5
463		4-5
464		4-5
465		4-5
466		4-5
467		4-5
468		4-5
469		4-5
470		4-5
471		4-5
472		4-5
473		4-5
474		4-5
475		4-5
476		4-5

¹ Lichtechtheit nach Xenon-Test ISO 105-B02 / Light fastness after Xenon-Test ISO 105-B02